



VIEW

Syntoliss – RAL 9022 | Light grey pearl
SYNTOLISS | RAL & NCS
Walo Bertschinger

<http://walo.ch> | bodenbelaege@walo.ch

Type: **Plastic | Synt. resin**

Synthetic floor cover | Real colour Samples > Request

mtextur ID	29240
Manufacturer	Walo Bertschinger
Manufacturer-Email	bodenbelaege@walo.ch
Product Line	SYNTOLISS RAL & NCS
Material Name	Syntoliss – RAL 9022 Light grey pearl
Type	Plastic / Synt. resin
Material Info	Synthetic floor cover Real colour Samples > Request
eBKP	G 2.2 Bodenbelag / G 2.2 Finished floor coverings
IFC	IfcCovering / IfcSlab.Floor
Area of application (mtextur Classic)	Inside / Floor
Delivery zones	CH / DE / LI
Size of the CAD & BIM texture	Height: 500.0 mm / Width: 500.0 mm

IMPORTANT LEGAL INFORMATION FOR USAGE OF THE MTEXTUR-DATABASE AND MTEXTUR DATASHEET:

In the mtextur-database and the mtextur-datasheet you can find a variety of high-quality digitalized materials, classified according material-type and subtype, color scope, field of application, manufacturer and product-line. The liability of the colors and the pattern of a CAD-texture can not always be guaranteed. For binding samples and additional questions please get in contact with the manufacturer or reseller directly (request link on material page). The information found on the mtextur-database is carefully collected and tested. Nevertheless are there possibilities for mistakes or wrong information. The publisher, h2c GmbH, the according manufacturers and resellers are not liable for any missing or incorrect information and its outcome, except h2c GmbH acts insofar willful.

max. Length / Format	Thickness = 3 mm
min. Format	Thickness = 2 mm
Characteristics Info	<p>Epoxidharz. Hohe Abrasions- und Druckfestigkeit, porenfreie, glatte und glänzende Oberfläche. Auch mit Mattversiegelung erhältlich. Gute Resistenz gegen Säuren, Laugen und Lösemittel. Farben nach RAL oder NCS möglich. d = 2–3 mm.</p> <p>Résine époxyde. Grande résistance à l'abrasion et la pression, exempt de pores, surface plane et brillante. Disponible aussi avec vitrification mate. Bonne résistance aux acides, solutions alcalines et solvants. Couleurs selon RAL ou NCS disponibles. Epaisseur = 2 à 3 mm.</p> <p>Resina epossidica. Elevata resistenza all'abrasione e alla compressione, superficie senza pori, liscia e brillante. Disponibile anche con sigillatura opaca. Buona resistenza ad acidi, soluzioni alcaline e solventi.</p> <p>Possibilità di tinte a norma RAL o NCS. d = 2–3 mm.</p>

IMPORTANT LEGAL INFORMATION FOR USAGE OF THE MTEXTUR-DATABASE AND MTEXTUR DATASHEET:

In the mtextur-database and the mtextur-datasheet you can find a variety of high-quality digitalized materials, classified according material-type and subtype, color scope, field of application, manufacturer and product-line. The liability of the colors and the pattern of a CAD-texture can not always be guaranteed. For binding samples and additional questions please get in contact with the manufacturer or reseller directly (request link on material page). The information found on the mtextur-database is carefully collected and tested. Nevertheless are there possibilities for mistakes or wrong information. The publisher, h2c GmbH, the according manufacturers and resellers are not liable for any missing or incorrect information and its outcome, except h2c GmbH acts insofar willful.