



fabromont
INSPIRED BY PEOPLE

VIEW

berber 774
Abraxas COLORpunkt & Abraxas
Fabromont AG

<https://www.fabromont.ch> | kundendienst@fabromont.ch

Type: Kugelgarn- & fleece | Kugelvlies

Kugelvlies

KUGELVLIES® – Der kleine Bruder des Kugelgarn®. Die Oberfläche besteht aus einem Faservlies, in welches einzelne Faserkugeln eingestreut werden. Komfortwert „einfach“. Strapazierwert „extrem“.

mtextur ID	81126
Manufacturer	Fabromont AG
Manufacturer-Email	kundendienst@fabromont.ch
Product Line	Abraxas COLORpunkt & Abraxas
Product Line Info	KUGELVLIES® – Der kleine Bruder des Kugelgarn®. Die Oberfläche besteht aus einem Faservlies, in welches einzelne Faserkugeln eingestreut werden. Komfortwert „einfach“. Strapazierwert „extrem“.
Material Name	berber 774
Type	Kugelgarn- & fleece / Kugelvlies
Material Info	Kugelvlies
eBKP	G 2.2 Bodenbelag / G 2.2 Finished floor coverings
IFC	IfcCovering / IfcSlab.Floor
Area of application (mtextur Classic)	Inside / Floor
Delivery zones	CH / DE / LU / NL / AT / LI
Size of the CAD & BIM texture	Height: 500.0 mm / Width: 500.0 mm

IMPORTANT LEGAL INFORMATION FOR USAGE OF THE MTEXTUR-DATABASE AND MTEXTUR DATASHEET:

In the mtextur-database and the mtextur-datasheet you can find a variety of high-quality digitalized materials, classified according material-type and subtype, color scope, field of application, manufacturer and product-line. The liability of the colors and the pattern of a CAD-texture can not always be guaranteed. For binding samples and additional questions please get in contact with the manufacturer or reseller directly (request link on material page). The information found on the mtextur-database is carefully collected and tested. Nevertheless are there possibilities for mistakes or wrong information. The publisher, h2c GmbH, the according manufacturers and resellers are not liable for any missing or incorrect information and its outcome, except h2c GmbH acts insofar willful.

max. Length / Format	Length = 50000 mm / Width = 2000 mm / Thickness = 4 mm
Weight	1.2 kg/m ²
Fire protection class	Cfl-s1
Characteristics Info	Trittschallverbesserungsmass: ca. 20 dB. Gültig für Betondecken. Verlangen Sie zusätzliche Informationen, wenn eine andere Unterkonstruktion eingesetzt wird. Antistatisch < 2.0 kV ableitfähige Variante mit RD < 108 Ω. Wärmedurchlasswiderstand ca. 0,08 m2. K/W. Zertifikate: EPD, TÜV PROFICERT, GuT und PRODIS, Swiss Made.

IMPORTANT LEGAL INFORMATION FOR USAGE OF THE MTEXTUR-DATABASE AND MTEXTUR DATASHEET:

In the mtextur-database and the mtextur-datasheet you can find a variety of high-quality digitalized materials, classified according material-type and subtype, color scope, field of application, manufacturer and product-line. The liability of the colors and the pattern of a CAD-texture can not always be guaranteed. For binding samples and additional questions please get in contact with the manufacturer or reseller directly (request link on material page). The information found on the mtextur-database is carefully collected and tested. Nevertheless are there possibilities for mistakes or wrong information. The publisher, h2c GmbH, the according manufacturers and resellers are not liable for any missing or incorrect information and its outcome, except h2c GmbH acts insofar willful.